

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B01D 15/08, B01J 20/00, 8/18, 8/10, B01D 15/02		A1	(11) International Publication Number: WO 99/51316 (43) International Publication Date: 14 October 1999 (14.10.99)
(21) International Application Number: PCT/US99/07480 (22) International Filing Date: 5 April 1999 (05.04.99) (30) Priority Data: 60/080,837 6 April 1998 (06.04.98) US (71) Applicant: BIOSEPPRA INC. [US/US]; 111 Locke Drive, Marlborough, MA 01752 (US). (72) Inventors: VOUTE, Nicolas; 2, rue de Pontoise, F-78780 Maurecourt (FR). BOSCHETTI, Egisto; 9, allée du Bois Gougenot, F-78720 Croissy sur Seine (FR). GIROT, Pierre; 7, rue du Terrage, F-75010 Paris (FR). (74) Agents: LAWRENCE, Stanton, T., III et al.; Pennie & Edmonds LLP, 1155 Avenue of the Americas, New York, NY 10036 (US).			(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: SMALL DENSE MICROPOROUS SOLID SUPPORT MATERIALS, THEIR PREPARATION, AND USE FOR PURIFICATION OF LARGE MACROMOLECULES AND BIOPARTICLES			
(57) Abstract The present invention provides small, dense mineral oxide solid supports or microbeads, comprising dense microporous mineral oxides matrices in which a skin of polymers is rooted, and their use in downstream processing, especially for fluidized bed purification of bioparticles or high molecular weight macromolecules.			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon	KR	Republic of Korea	PL	Poland		
CN	China	KZ	Kazakhstan	PT	Portugal		
CU	Cuba	LC	Saint Lucia	RO	Romania		
CZ	Czech Republic	LI	Liechtenstein	RU	Russian Federation		
DE	Germany	LK	Sri Lanka	SD	Sudan		
DK	Denmark	LR	Liberia	SE	Sweden		
EE	Estonia			SG	Singapore		

**Small Dense Microporous Solid Support Materials, Their Preparation,
and Use For Purification of Large Macromolecules and Bioparticles**

Field of Invention

5 The present invention relates to solid supports for purification of bioparticles or high molecular weight macromolecules.

Background of the Invention

High molecular weight ("HMW") macromolecules such as nucleic acids, polysaccharides, protein aggregates, and bioparticles such as viruses, viral vectors,
10 membrane proteins and cellular structures, are difficult to isolate from biological sources due to their physical characteristics. Classical techniques for isolating HMW macromolecules and bioparticles include gradient density centrifugation, microfiltration, ultrafiltration and chromatography. These methods present a number of practical disadvantages. Gradient density centrifugation is a time consuming and
15 energy intensive process and provides only limited purification due to intrinsic molecular or bioparticle heterogeneities. (Green *et al.*, "Preparative purification of supercoiled plasmid DNA for therapeutic applications," *Biopharm*, pp. 52-62 (May 1997).) Membrane technologies, such as cross flow filtration, require a substantial shear stress to maintain permeate flux and these levels of sheer stress are prejudicial to
20 the integrity of the molecules or particles and consequently to their biological activities. (Braas *et al.*, "Strategies for the isolation and purification of retroviral vectors for gene therapy," *Bioseparation*, 6:211-228 (1996).)

Packed bed chromatography and adsorption of large molecular weight molecules or particles are also hampered by the physical characteristics of these
25 compounds, setting stringent limitations in terms of operating bed capacity and pressure drop.

On the one hand, these large biological structures do not penetrate into classical gel media commonly used in bioseparation and, as a consequence, these large biological structures do not access the internal surface area and pore volume, where
30 the majority of the adsorptive sites are located. Therefore, the partitioning between mobile and liquid phase and the binding capacity is inherently limited. On the other hand, there is no interest in producing media with pores large enough to accommodate these large or HMW biological structures because the intraparticle diffusion in the

pores of such media would be extremely limited due to their large size. Consequently the mass transfer and the productivity of such media would be low.

Therefore, chromatography and adsorption of very large molecular weight molecules and bioparticles are hampered by a screening effect, independent of the mode of adsorption. If adsorption of the target HMW compounds occurs, it is restricted only to the external surface area of sorbent beads, and therefore yields low binding capacities. This mode of operation, known as positive adsorption, is rarely used due to this very low binding capacity.

Direct recovery of large macromolecules in the flowthrough of solid phase beds is known as negative solid phase purification. HMW compounds flow through the column without being delayed, while smaller contaminants, like proteins, amino acids, sugars and salts, diffuse in the intraparticle volume of the solid phase porous beads, where they can be delayed or adsorbed. This approach shows numerous drawbacks detrimental to performance of separations. First, if separation is based on size exclusion, the loading and the operational linear velocity are very low, dramatically reducing the column productivity. In addition, if separation is based on adsorption, large resin volumes are required as all the contaminants must diffuse and be adsorbed into the beads. Furthermore, negative purification processes do not offer any selectivity between different types of very large macromolecules, as they co-elute in the flowthrough. In particular, it is impossible to segregate plasmids from genomic DNA and large RNA molecules using negative chromatography purification processes.

As an intermediate case between positive and negative adsorption processes, the operating conditions can be set such that both the HMW compounds and the contaminants are adsorbed. In this situation, flowthrough of the target component (such as a very large macromolecule) will occur only after the initial saturation of the external surface of the beads. Such conditions, however, lead to a decrease in target component recovery.

In addition, solutions of HMW biopolymers (such as nucleic acids and polysaccharides) and bioparticles tend to have a high viscosity. In turn, the high viscosity impairs purification of these compounds in many ways; for example:

- it reduces the diffusivity of the compounds, and therefore tremendously reduces boundary layer and intraparticle mass transfer rate; and

it increases the hydraulic resistance of a fixed bed column and generates large pressure drops.

The augmentation of mass transfer resistance is extremely prejudicial to the adsorbent capture efficiency. Longer residence times can potentially counterbalance the reduced rate of adsorption. In order to achieve such longer residence time, however, it would be necessary to use very low linear velocity or very long columns. Both strategies are impracticable as they result in very long purification cycle time and increased pressure drop.

Large pressure drops generated by high viscosity samples, such as those containing HMW macromolecules, restrict the use of semi-rigid adsorbents as these semi-rigid adsorbents are deformed under the mechanical strain and lead to clogging of the column. In order to reduce the pressure drop, extremely low flow rates or very large particle diameter could be used. However, at the preparative level, both solutions are unrealistic because they lead to large cycle time on the one hand, and very low binding capacity due to too small interactive surface area of large bioparticles on the other hand.

Furthermore, solid particles injected through a packed bed of beads are progressively trapped in the intraparticle spaces where they accumulate and tend to irreversibly clog the column.

Some of the problems associated with high viscosity samples and the presence of particulates in a feed stock can be circumvented by using a stirred tank. However, the solid and liquid mixing using stirred tank contactors restrict the capture efficiency. Compared to a fixed bed, the productivity of a stirred tank is reduced due to the low concentration of the adsorbent in the contactor. Moreover, semi-open systems, such as stirred tanks, are difficult to clean, sanitize and automate.

Fluidized bed contactors are also an alternative means for processing high viscosity samples and samples containing insoluble particles. (See, e.g., Buijs and Wesselingh, "Batch Fluidized ion-exchange column for stream containing suspended particles," *J. Chrom.*, 201:319-327 (1980); Chase "Purification of proteins by adsorption chromatography in expanded beds," *Tibtec*, 12:296-303 (1994); Somers *et al.*, "Isolation and purification of endo-polygalacturonase by affinity chromatography in a fluidized bed reactor," *Chem. Eng. J.*, 40: B7-B19 (1989); and Wells *et al.*, "Liquid fluidized bed adsorption in biochemical recovery from biological suspensions,"

Separation for Biotechnology, M. Verall, ed., Ellis Harwood; Chicester, pp. 217-224 (1987).) However, the media or adsorbents commercially available at present are inadequate for the purification of HMW molecules and particles. (See US Pat. No. 5,522,993 and European patents EP 0 538 350 B1, EP 0 607 998 B1.) The internal
5 porosity of these media or adsorbents is inaccessible for very large solutes, and their large particle diameter undesirably decreases the external surface area. As a result, these media provide only limited capacity for the purification of HMW molecules and particles.

Fluid bed separation processes are attractive for the recovery of bioproducts as
10 they achieve lower operational pressures than a packed bed and are resistant to fouling by particulates and suspended materials in the feed stock. Fluidized-bed technology has been successfully employed as early as 1958 for the recovery of small molecules, such as antibiotics. (See Bartels *et al.*, "A novel ion exchange method for the isolation of streptomycin," *Chem. Eng. Prog.*, 54(8):49-51 (1958); Belter *et al.*, "Development
15 of a recovery process for novobiocin," *Biotechnol.Bioeng.*, 15:533-549 (1973).) More recently, this technology has been applied for the recovery of larger molecular weight molecules, such as proteins, from unclarified feed stocks. (See, A. Bascoul, "Fluidisation liquide-solide. Etude hydrodynamique et extraction des proteines,"
These d'etat, Universite Paul Sabatier, Toulouse, France (1989); B. Biscans,
20 "Chromatographie d'echange d'ions en couche fluidisee. Extraction des proteines du lactoserum," These de docteur ingenieur, Institut national polytechnique de Toulouse, Toulouse, France (1985); Biscans *et al.*, *Entropie*, 125/126: 27-34 (1985); Biscans *et al.*, *Entropie*, 125/126: 17-26 (1985); Draeger and Chase, "Liquid fluidized bed adsorption of protein in the presence of cells," *Bioseparation*, 2: 67-80 (1991);
25 Draeger and Chase, "Liquid fluidized beds for protein purification," *Trans IChemE*, 69(part C): 45-53 (1991); J. van der Weil, "Continuous recovery of bioproducts by adsorption," PhD Thesis, Delft University, Delft (1989); and Wells *et al.*, "Liquid fluidized bed adsorption in biochemical recovery from biological suspensions."
Separation for Biotechnology, M. Verall, ed., Ellis Harwood, Chicester, pp. 217-224
30 (1987).)

US Pat. No. 4,976,865 describes a method and a column for fluidized bed chromatographic separation of samples containing molecules which have a tendency towards autodenaturation, including biopolymers of medium molecular weight, such as

proteins, enzymes, toxins and antibodies. This method assumes that any suspended material in the sample or feed stock is removed during loading and washing, while the molecules of interest diffuse inside the adsorbent loaded in the column. However, the operational binding capacity of the procedure and materials describe in US Pat.

- 5 No. 4,976,865 are inadequate for the biopurification of HMW molecules and bioparticles.

US Pat. No. 5,522,993 and European patents EP 0 538 350 B1, EP 0 607 998 B1, describe special polymeric resin media, especially agarose, having small particles of dense materials within the media, and their use in fluidized beds. The dense material
10 described for use trapped within the polymeric resin media include glass, quartz and silica. However, despite the gain in density of this media due to the presence of the small particles of dense material, the density is still relatively low, and thus in order to achieve a stabilized fluidized bed, large bead diameter is required to compensate for the low density differential between the liquid and solid phases. European patents
15 EP 0 538 350 B1, EP 0 607 998 B1 also describe beads which consist of a porous conglomerate of polymeric material and density controlling particles therein. The beads described in these three patents are inadequate for the isolation of HMW molecules and bioparticles as the low density and the large particle size of these beads are not conducive to separation of HMW macromolecules and bioparticles.

20 **Summary of the Invention**

The present invention provides new dense mineral oxide solid supports or microbeads which exhibit high density, low porosity, high external surface area and high binding capacity. The small dense mineral oxide solid supports or microbeads of the present invention may be used in various solid phase adsorption and
25 chromatography methods including packed bed and fluidized bed methods, and are particularly useful in fluidized bed devices and allow higher linear velocities to be used in such fluidized bed devices. These solid supports or microbeads are particularly suited for separating or isolating large biological molecules, such as bioparticles and high molecule weight macromolecules, especially in fluidized bed or expanded bed
30 methods.

Accordingly, one object of the present invention concerns dense mineral oxide solid supports or microbeads comprising a) a mineral oxide matrix having a pore volume which is less than 30% of the total volume of the mineral oxide matrix, and b)

an interactive polymer network which is rooted in pores of the mineral oxide matrix. The dense mineral oxide solid supports or microbeads of the present invention have densities of about 1.7 to 11, and preferably from about 2.1 to about 10, and particle sizes within the range of about 5 μm to 500 μm , and preferably in the range of about 10 μm to 100 μm .

The mineral oxide matrix may comprise particles of one mineral oxide, or any combination of two or more mineral oxides. Preferably, the mineral oxide matrix is comprised of particles of very dense mineral oxides, such as titania, zirconia, yttria, ceria, hafnia, tantalum, and the like, or mixtures thereof. The particle size of the mineral oxide starting materials may be varied depending on the surface characteristics desired, and typically for relatively smooth mineral oxide matrix surfaces, particle sizes in the range of about 0.1 μm to 3 μm are used, and for rougher mineral oxide matrix surfaces, particle sizes in the range of about 3 μm to 15 μm are used.

The interactive polymer network may comprise copolymerized monomers, bifunctional monomers, or combinations thereof, or crosslinked synthetic linear polymers, natural organic polymers, or combinations thereof, and the components used to form the interacting polymer network are selected in order to confer a predetermined property or properties to the resulting polymer network. The interacting polymer network components may be selected such that the resulting polymer network has affinity for a desired target molecule, or such that the resulting polymer network has a predetermined property or properties which allow the polymer network to be subsequently functionalized or derivatized to have affinity for a desired target molecule using techniques well known to the skilled artisan.

Another object of the present invention concerns use of the novel dense mineral oxide solid supports or microbeads described herein in solid phase adsorption and chromatography methods. Accordingly, the present invention also relates to a method for separating a desired biological molecule from a sample containing the same comprising loading a chromatography device with a chromatography bed comprised of dense mineral oxide solid supports or microbeads comprising a) a mineral oxide matrix having a pore volume which is less than 30% of the total volume of the mineral oxide matrix, and b) an interactive polymer network which is rooted in pores of the mineral oxide matrix, feeding the sample containing said desired biological molecule into the

chromatography device, discharging undesired components and impurities of the sample from the chromatography device, releasing the desired biological molecule from the dense mineral oxide solid supports and eluting the desired biological molecule from the chromatography device. The interactive polymer network of the dense mineral oxide solid supports used in this method is prepared such that it has affinity for the desired biological molecule, or the interactive polymer network may be functionalized or derivatized to have affinity for the desired biological molecule. In addition, when the sample is fed into the chromatography device, the desired biological molecule is adsorbed to the dense mineral oxide solid supports or microbeads.

Yet another object of the present invention concerns a fluid bed method for chromatographically separating a desired biological molecule from a sample containing the same comprising providing a fluid bed reactor or column with a chromatography bed comprised of dense mineral oxide solid supports comprising i) a mineral oxide matrix having a pore volume which is less than 30% of the total volume of the mineral oxide matrix, and ii) an interactive polymer network which is rooted in pores of the mineral oxide matrix, creating a fluidized bed of said dense mineral oxide solid supports in said fluid bed reactor or column, feeding the sample containing said desired biological molecule into the fluid bed reactor or column under conditions which maintain the dense mineral oxide solid supports in the fluidized bed, discharging undesired components and impurities of the sample from the fluid bed reactor or column, and effecting the release of the desired biological molecule from the dense mineral oxide solid supports and eluting the desired biological molecule from the fluid bed reactor or column. The interactive polymer network of the dense mineral oxide solid supports used in this method is prepared such that it has affinity for the desired biological molecule, or the interactive polymer network may be functionalized or derivatized to have affinity for the desired biological molecule. In addition, when the sample is fed into the fluid bed reactor or column, the desired biological molecule is adsorbed or attached to the dense mineral oxide solid supports or microbeads.

These and other objects of the present invention will become apparent to those skilled in the art from a reading of the instant disclosure.

Detailed Description of the Invention

Classical chromatography media and their methods of use are inadequate for the purification of HMW macromolecules and large molecular entities. The present invention provides adsorbents (also referred to herein as "solid supports" or "microbeads") having a small particle diameter and high density which provide large binding capacity for HMW compounds and can be operated in a low pressure drop, high throughput fluid bed process. Furthermore, the microbeads of the present invention can be modified by functionalized polymers or monomers enabling the exploitation of high selectivity separation.

According to the present invention very large or HMW macromolecules or bioparticles can be separated using solid particles of small diameter and very high density. These particles are designed to be used in suspension, and in particular, in fluid bed modes. Unlike packed bed columns, fluidized bed contactors exhibit low hydraulic resistance and are not impeded by pressure drop limitation or fouling.

Existing typical fluid bed particles include porous gel materials having particle diameters of typically 100-300 μm and mean particle density of about 1.2 g/ml. (See Batt *et al.*, "Expanded bed adsorption process for protein recovery from whole mammalian cell culture broth," *Bioseparation*, 5: 41-52 (1995).) These materials are not suited for the separation of very large or HMW macromolecules and bioparticles as these components do not diffuse within the pores or gel network of the media and adsorb only on the external surface area of the media. Due to the large diameter of existing fluidized-bed gel particles, the external surface area of a given amount of bead volume yields only a modest value, and as a result the binding capacity is very small. Moreover, gel-type materials offer only limited density, typically within 1.1 to 1.3 g/cm³. These low densities set stringent limitations in terms of operating velocity that limit the productivity of the column.

Rather than enlarging the pore volume allowing the HMW macromolecules or particles to diffuse, according to present invention the particle size of the beads are decreased and the surface area is increased due to the diminution of the average particle diameter. The surface area per unit volume of a bed of spherical particles varies proportionally with the inverse of the particle diameter. Therefore, by decreasing the particle size, the surface area of media is advantageously increased, thereby increasing the binding capacity for a given molecule.

However, when dealing with a fluid bed, the usefulness of small diameter gel-based beads is limited by the terminal velocity of the solid material. The particle terminal velocity, *i.e.*, the velocity at which the beads are ejected from the column by an upward liquid flow, depends on the square of the particle diameter times the density differential between solid and liquid phases. For small and light beads the particle terminal velocity is so low that operation in fluid bed mode would require an unrealistically small operating velocity in order to keep the beads from leaving the column. That is, small gel based particles, which have low densities, would be ejected from the column or contactor even at modest fluidization velocities, *e.g.*, less than about 50 cm/hour. Therefore, large bead diameters must be used with these beads to compensate for the low density differential between the liquid and the solid phases; however, large particle diameters result in lower binding capacity for the media.

This problem is overcome according to the present invention by using small diameter particles made using novel solid materials which exhibit a very high density that permits fluidization of these small diameter particles or microbeads even at elevated velocities. Thus, in the solid supports or microbeads according to the present invention, high external surface area, and consequently high binding capacity, resulting from small particle diameter is combined with a high bead or particle solid density which allows rapid process velocities to be used in methods using these solid supports or microbeads according to the present invention.

The solid support materials or adsorbents of the present invention are made using very dense mineral oxides such as titania, zirconia, yttria, ceria, hafnia, and tantalum, or mixtures thereof. Unlike classic porous mineral oxide based materials for chromatographic application, the solid support materials or adsorbents of the present invention have low pore volume so that the apparent density of the materials is a large fraction of the intrinsic material density. In the solid support materials or adsorbents of the present invention, the pore volume is lower than about 30 % of total bead volume, and preferably the pore volume is 5% to 25%, and more preferably 5% to 15%, of the total volume of the bead volume. The pore volume of the solid support materials or adsorbents can be modulated by adequate temperature treatment.

In the solid support materials or adsorbents of the present invention, the pore volume is left just large enough to allow polymers to be rooted in the pores, and these rooted polymers layer on the external surface of the beads where the interaction with

the macromolecules occurs. The resulting layer of polymers, or interactive polymer network, is stable and remains in place. The interaction of the desired molecules occurs on the external surface area of the beads due to the rooted polymers.

Mineral oxide matrices or microbeads for use in the present invention are prepared by methods which allow condensing of small particles of mineral oxide or condensing of salt soluble molecules of heavy elements. A variety of techniques known to the skilled artisan, such as emulsion/suspension techniques, spray-drying, or sol-gel methods (as described, for example, in U.S. Pat. No. 5,015,373), may be used to effect the agglomeration of the compositions described in the present invention.

In general, microparticles of a mineral oxide (e.g., titania powder or zirconia powder, or the like) having a diameter in the range of 0.1 μm to 15 μm are suspended in a water solution containing soluble sodium silicate at alkaline pH, and the solution is poured into an oil bath under stirring to obtain a suspension of droplets that contain microparticles of the mineral oxide. Once the oil suspension is acidified with an organic acid, sodium silicate forms a gel (the liquid droplet is turned into a gel particle) that entraps the solid microparticles of dense mineral oxide. These gelified microbeads are then separated from the oil using well-known physical means and are dried at about 80°C- 200°C. The gel hardening process allows the conglomerate of small particles to stabilize. Moreover, an inter small particle porosity or intra-bead porosity appears due to the reduction of the gel volume. At this stage, the pore volume is between about 30% to 70% of the bead volume.

The resulting beaded porous mineral oxide particles are then fired at a high temperature, e.g., in the range of about 900°C to 1500°C, and preferably between about 1000°C to 1400°C, for a period of about 1 to 12 hours so as to melt the submicroparticles together and reduce the particle diameter and reduce the pore volume to less than about 30%. The firing temperatures and times are dependent on the nature of the mineral oxide(s) used as the starting material, and can be readily determined by the skilled artisan.

The dried low porosity mineral oxide particles are then impregnated with a solution of functionalized monomers or polymers and crosslinkers by adding the dried low porosity mineral particles to a monomer solution, wherein the amount of the monomer solution is in excess the pore volume of the porous mineral material,

preferably by about 5% to 10%, and starting the polymerization. The polymerization of the organic products is accomplished by means of chemical inducers, including but not limited to well known chemical catalysts associated or not to physical inducers, such as intense UV light or any other form of irradiation such as gamma irradiation or
5 microwaves. Temperature may also be used to induce crosslinking or copolymerization of the monomer solution. A desired functionalization of the polymers is obtained by selecting the appropriate monomers before polymerization, or by classical chemical reactions on the organic layer after polymerization.

As an example, according to the present invention, hafnia mineral oxide
10 matrices or microbeads may be made by various means known in the art that generally yield materials having a pore volume of between 30 to 70% of the total bead volume. Thereafter, the resulting hafnia beads are fired at 1200 to 1400°C for about 2 to 4 hours in order to collapse the pore volume and increase the specific density of the beads. As a result, the initial pore volume of about 30% to 70% is decreased to about
15 10% to 20%.

After firing the base mineral oxide solid support materials or mineral oxide matrices, a solution containing a mixture of monomers, which include an appropriate ligand or appropriate linker, is injected in the pore volume of the resulting low pore volume hafnia beads and is copolymerized in the presence of crosslinkers. The
20 impregnation volume of the monomer solution should be a little higher, *e.g.*, 1% to 10% higher, and preferably 5% to 10% higher, than the pore volume of the beads such that the functionalized polymer is anchored or rooted in the internal porosity and is also present, as a thin layer, on the external surface of the dense solid support materials or microbeads.

25 Solid supports or adsorbents made in accordance with the present invention may then be separated, washed and used in various chromatographic techniques, and in particular, the small, dense solid supports or microbeads can be used in fluid bed devices in order to process and separate biological molecules or bioparticles of interest, including very large macromolecules and bioparticles.

30 The interacting polymer networked with the mineral oxide matrix of small, dense solid supports or microbeads of the present invention may comprise hydrophobic or hydrophilic polymers or both. The polymeric structures can be

obtained by polymerization of monomers under specified conditions or can be the result of crosslinking linear soluble polymers.

In the case where monomers are copolymerized on the surface of the mineral oxide particles or beads with some rooting inside the pores, the initial impregnating solutions can be composed of monomers from different families, such as acrylic monomers, vinyl compounds, and allyl monomers, or a mixture thereof. Typical monomers for use in the present invention, include but are not limited to, the following:

- Aliphatic ionic, non-ionic and reactive derivatives of acrylic, methacrylic, vinylic and allylic compounds such as, but not limited to, acrylamide, dimethylacrylamide, trisacryl, acrylic acid, acryloylglycine, diethylaminoethylmethacrylamide, vinylpyrrolidone, vinylsulfonic acid, allylamine, allylglycidylether, or derivatives thereof, and the like;

- Aromatic ionic, non-ionic and reactive derivatives of acrylic, methacrylic, vinylic and allylic compounds, such as, but not limited to, vinyltoluene, phenylpropylacrylamide, trimethylaminophenylbutylmethacrylate, tritylacrylamide, or derivatives thereof, and the like;

- Heterocyclic ionic, non-ionic and reactive derivatives of acrylic, methacrylic, vinylic and allylic compounds, such as, but not limited to, vinylimidazole, vinylpyrrolidone, acryloylmorpholine, or derivatives thereof, and the like.

Bifunctional monomers may also be used in forming the interactive polymer network of the solid supports or microbeads of the present invention in order to increase the stability of the gel structures. Bifunctional monomers suitable for use in the present invention are those containing double polymerizable functions, such as two acrylic groups, that react with other monomers during the process of forming the interactive polymer network structure. More specifically, monomers which may be used in forming the interacting polymer network of the solid support materials or microbeads of the present invention include, but are not limited to, the following:

- Bisacrylamides, such as, but not limited to, methylene-bis-acrylamide, ethylene-bis-acrylamide, hexamethylene-bis-acrylamide, glyoxal-bis-acrylamide, and the like;

- Bis-methacrylamides, such as, but not limited to, methylene-bis-methacrylamide, ethylene-bis-methacrylamide, hexamethylene-bis-methacrylamide, and the like;

- Bis-acrylates, such as, but not limited to, diethylglycoldiacrylate, diethylglycolmethacrylate, ethyleneglycoldiacrylate, ethyleneglycoldimethacrylate, and the like;

- Ethyleneglycol-methacrylates, and the like; and

- Diallyltartradiamide.

The monomers, bifunctional monomers, or combinations thereof, selected to form the interactive polymer network of the solid supports or microbeads of the present invention confer a predetermined property or properties to the resulting polymer network. A polymerized or crosslinked gel network rooted in the pores is formed and layered over the surface of the beads. Properties which are of primary interest for the solid support materials or compositions of the present invention include, but are not limited to, ion exchange effects, hydrophobic association, reverse phase interaction, biospecific recognition, and all intermediates of such, or combinations of two or more of these properties

Soluble organic polymers, such as linear polymers from synthetic or natural sources, may also be used to fill the pore volume and coat the external surface area of the mineral oxide dense beads of the present invention. The synthetic and natural soluble polymers are crosslinked in place (on the surface and inside the pore structure of the mineral oxide beads or particles) by classical chemical and physical means, e.g., by chemical bifunctional crosslinkers, such as but not limited to, bisepoxy reagents, bisaldehydes, and the like. After such polymers are crosslinked, a stable gel network is formed which is anchored or rooted in the pores and layered on the surface of the mineral oxide matrix of the solid supports or microbeads of the present invention.

Crosslinking agents useful in the present invention include vinyl monomers having at least one other polymerizable group, such as a double bond, a triple bond, an allylic group, an epoxide, an azetidine, or a strained carbocyclic ring. Preferred crosslinking agents include, but are not limited to, N,N'-methylene-bis-(acrylamide), N,N'-methylene-bis-(methacrylamide), diallyl tartradiamide, allyl methacrylate, diallyl amine, diallyl ether, diallyl carbonate, divinyl ether, 1,4-butanedioldivinylether, polyethyleneglycol divinyl ether, and 1,3-diallyloxy-2-propanol.

Synthetic linear polymers which may be used in the present invention include, but are not limited to, polyethyleneimines, polyvinyl alcohol, polyvinylamines, polyvinylpyrrolidone, polyethyleneglycols, polyaminoacids, nucleic acids, and their derivatives. Natural soluble polymeric molecules which may be used in the present invention include, but are not limited to, polysaccharides, such as agarose, dextran, cellulose, chitosans, glucosaminoglycans and their derivatives, and nucleic acids.

The small, dense mineral oxide solid supports or microbeads of the present invention may be used advantageously in various chromatography methods which may be carried out in a fluidized bed mode, a packed bed mode, or other modes of operation. The solid supports or microbeads of the present invention are particularly useful in methods for separating or isolating a desired molecule or bioparticle of interest from a crude sample with a fluidized bed mode of operation.

Methods for separating or purifying desired macromolecules or target molecules of interest from a sample typically involve at least two steps. The first step is to charge a chromatography device, such as a packed or fluidized bed column, containing the mineral oxide solid supports or microbeads of the present invention with a solution containing a mixture of biomolecules, at least one of which is the target molecule of interest. The second step is to pass an eluent solution or elution buffer through said chromatography device to effect the release of the target molecule of interest from the solid supports or microbeads and the chromatography device, thereby causing the separation of the target molecule from the sample.

"Stepwise" elution can be effected, for example, with a change in solvent content, salt content or pH of the eluent solution or elution buffer. Alternatively, gradient elution techniques well known in the art can be employed. Elution buffers or eluent solutions suitable for use in the present invention are well known to those of ordinary skill in the art. For example, a change in ionic strength, pH or solvent composition may effect release of a molecule which is bound to a solid phase support. Elution buffers or eluent solutions may comprise a salt gradient, a pH gradient or any particular solvent or solvent mixture that is specifically useful in displacing a desired macromolecule or target molecule of interest.

For methods of separating or isolating a desired macromolecule in fluidized bed devices, the small, dense solid support materials or microbeads of the present invention functionalized with an interactive polymer network having an affinity for the desired

macromolecule are loaded into a fluid bed device, and a sample or a feed stock containing the desired macromolecule to be separated is fed into the fluid bed device. The sample or feed stock flows through the fluid bed device in an upward direction so as to lift the solid support materials or microbeads with limited pressure drop. The
5 desired macromolecules are in such a way adsorbed on the surface of small dense solid support materials or microbeads due to the functionality(ies) carried by the interactive polymer network of the beads, and thus impurities are separated by the continuous upward flow. Washing in the same direction is followed and adsorbed
10 macromolecules are desorbed by passing an eluent solution or elution buffer through the fluid bed device to effect separation of the desired macromolecule as a result of physicochemical changes, such as pH changes, ionic strength adaptation, or solvent composition, and other means well known to the skilled artisan.

Once the separation is completed, the solid supports or microbeads are washed extensively to eliminate all very tightly adsorbed biological materials, and
15 reequilibrated in the appropriate solution so that another separation cycle can be initiated.

The methods of the present invention are effective to isolate or separate a broad range of large biological molecules, including proteins (such as thyroglobulin, $\alpha 2$ macroglobulin, antibodies of IgG and IgM classes, and the like), carbohydrates
20 (such as hyaluronic acid), bioparticles (such as viruses, viral vectors, membrane proteins, cellular structures, and the like), and nucleic acids (such as plasmids, DNA, RNA, large oligonucleotides, and the like). The solid supports or microbeads of the present invention are particularly useful in methods for separating or isolating high
25 molecular weight macromolecules, such as nucleic acids, plasmids, polysaccharides, protein aggregates, and bioparticles such as viruses, viral vectors, membrane proteins and cellular structures. Such methods are preferably performed in the fluidized bed mode of operation.

The main advantages of the small, dense solid support materials or microbeads of the present invention for use in the capture of high molecular weight
30 macromolecules and biological particles are as follows:

- a) the low particle size yields a high external surface area and consequently an increased binding capacity compared to traditional large porous gel based media;

- b) high external surface area binding allows for minimizing pore volume and maximizing the bead density;
- c) very dense beads allow high linear process velocities to be used in fluidized bed contactors or devices and low operating pressure even in the presence of viscous material, such as samples containing large macromolecules and bioparticles;
- d) very rapid mass transfer is possible due to the absence of intraparticle diffusion, *i.e.*, using the external surface area as the adsorption-eluting mechanism, the final collected volume is smaller than from conventional fixed or fluid bed technologies with existing porous materials, and thus the adsorption/elution kinetics are very rapid and adsorption can be performed at very low residence time with negligible loss of the target molecule in the effluent;
- e) adsorption of contaminants is reduced compared to traditional porous gel media, because the adsorption surface is confined to a small external layer and does not include the intraparticle volume;
- f) separation between different types of very large macromolecules is possible by adjusting the elution conditions.

Possible variations on the design of the small, dense mineral oxide solid support materials or microbeads of the present invention include, but are not limited to, changing the shape of external surface area of the materials, changing the composition of mineral oxides in the materials, and changing the composition of the interactive polymer network that is rooted in the mineral oxide matrix or base materials of the small, dense solid support materials or microbeads of the present invention. In addition, the surface of the mineral oxide solid phase or base material, where substantially all the macromolecules interact, can be smooth, or rough in order to increase the surface area, as shown in the examples below.

The invention is further defined by reference to the following examples that describe in detail the preparation of the small, dense solid supports or microbeads of the present invention and methods of using the same. It will be apparent to those skilled in the art that many modifications, both to materials and methods, may be practiced without departing from the purpose and scope of this invention.

Example 1:**Preparation of collapsed porous silica microbeads
with enhanced density by emulsion condensation**

30 grams of dry solid irregular silicon oxide (having particle sizes in the range
5 of 0.3-3 μm) were dispersed under stirring in 15 ml of a concentrated 35% sodium
silicate solution and then diluted with 20 ml of distilled water and 9 ml of acetic acid.
The resulting homogeneous suspension was slowly poured into an agitated paraffin oil
bath containing 2% of sorbitan sesquioleate and dispersed as small droplets.

The suspension was stirred for 1 hour at ambient temperature, and then heated
10 at 85°C for 1 hour.

Dispersed liquid droplets containing silicon oxide particles were thus turned
into gelled beads. The resulting gelled beads had an average diameter of 50 μm and
comprised a silica hydrogel having trapped within its network solid microparticles of
pre-formed solid silicon oxide. The gelled beads were recovered by filtration, washed
15 and dried at 80°C under air stream for 16 hours. During the drying, the hydrogel was
progressively dehydrated and acted to bind the solid silicon oxide microparticles. The
pore volume of resulting beads was about 1/3 of the bead volume. The beads were
then fired at 1100 °C for 2 hours. As a result of this firing, the bead sub-particles
were partially melted and fused to each other thereby reducing the pore volume. After
20 this treatment the final void pore volume represented about 10% of the whole bead
volume. The density of the dry beads was about 2.1 g/cm³.

The diameter of the bead and the distribution of the diameters are controlled by
the mechanical agitation of the paraffin oil bath and the amount of surfactant used.
Other means of emulsifications can be used to control the bead diameter.

25 The resulting dense solid support materials or microbeads may be subsequently
coated or filled with an interacting polymer network comprised of various organic
polymers in order to confer specific biomolecule adsorption properties to the solid
support materials or microbeads.

Example 2:

30 **Preparation of zircon (zirconium silicide)
microbeads with reduced pore volume**

Microbeads were prepared as described in Example 1 except that silicon oxide
solid irregular microparticles were replaced by zircon fine powder (having particle

sizes in the range of 0.1- 5 μm). The dried microbeads obtained with this methodology were then fired at 1400°C for 4 hours to reduce the initial pore volume (about 1/3 of bead volume) to about 10% of bead volume.

The density shown by these beads was about 4.2 g/cm³.

5 The resulting dense solid support materials or microbeads may be subsequently coated or filled with an interacting polymer network comprised of various organic polymers in order to confer specific biomolecule adsorption properties to the solid support materials or microbeads.

Example 3:

10 **Preparation of titania (titanium oxide)
microbeads with reduced pore volume**

Microbeads were prepared as described in Example 1 except that silicon oxide solid irregular microparticles were replaced by titanium oxide fine powder (having particle sizes in the range of 0.1- 10 μm). The resulting dried microbeads were then
15 fired at 1200 °C for 4 hours to reduce the initial pore volume (about 1/3 of bead volume) to about 15% of bead volume.

The density shown by these beads was about 3.5 g/cm³.

The resulting dense solid support materials or microbeads may be subsequently coated or filled with an interacting polymer network comprised of various organic
20 polymers in order to confer specific biomolecule adsorption properties to the solid support materials or microbeads.

Example 4:

**Preparation of hafnia (hafnium oxide)
microbeads with reduced pore volume**

25 Microbeads are prepared as described in Example 2 except that zircon fine powder is replaced by hafnium oxide fine powder. The dried microbeads obtained are then fired at 1400°C for 4 hours to reduce the initial pore volume (about 1/3 of bead volume) to about 10% of bead volume.

The density shown by these beads is about 8.5 g/cm³.

30 The resulting dense solid support materials or microbeads may be subsequently coated or filled with an interacting polymer network comprised of various organic polymers in order to confer specific biomolecule adsorption properties to the solid support materials or microbeads.

Example 5:**Preparation of tantalum oxide
microbeads with reduced pore volume**

Microbeads are prepared as described in Example 2 except that zircon fine
5 powder is replaced by tantalum oxide fine powder. The dried microbeads obtained are
then fired at 1400°C for 4 hours to reduce the initial pore volume (about 1/3 of bead
volume) to about 10% of bead volume.

The density shown by these beads is about 7.2 g/cm³.

The resulting dense solid support materials or microbeads may be subsequently
10 coated or filled with an interacting polymer network comprised of various organic
polymers in order to confer specific biomolecule adsorption properties to the solid
support materials or microbeads.

Example 6:**Preparation of zirconium oxide
15 microbeads with reduced pore volume**

Microbeads were prepared as described in Example 2 except that zircon fine
powder was replaced by zirconium oxide fine powder (having particle sizes in the
range of 0.1- 3 µm). The resulting dried microbeads were then fired at 1400°C for 4
hours to reduce the initial pore volume (about 1/3 of bead volume) to about 12% of
20 bead volume.

The density shown by these beads was about 5.2 g/cm³.

The resulting dense solid support materials or microbeads may be subsequently
coated or filled with an interacting polymer network comprised of various organic
polymers in order to confer specific biomolecule adsorption properties to the solid
25 support materials or microbeads.

Example 7:**Preparation of yttria (yttrium oxide)
microbeads with reduced pore volume**

Microbeads were prepared as described in Example 2 except that zircon
30 powder was replaced by yttrium oxide fine powder (0.1- 3 µm). The dried microbeads
obtained were then fired at 1400°C for 4 hours to reduce the initial pore volume
(about 1/3 of bead volume) to about 20% of bead volume.

The density shown by these beads was about 4.5 g/cm³.

The resulting dense solid support materials or microbeads may be subsequently coated or filled with an interacting polymer network comprised of various organic polymers in order to confer specific biomolecule adsorption properties to the solid support materials or microbeads.

5

Example 8:**Preparation of alumina (aluminum oxide)
microbeads with reduced pore volume**

Microbeads are prepared as described on Example 1 except that silicon oxide solid irregular microparticles are replaced by aluminum oxide fine powder. The
10 resulting dried microbeads are then fired at 1400°C for 4 hours to reduce the initial pore volume (about 1/3 of bead volume) to about 20% of bead volume.

The density shown by these beads is about 3.5 g/cm³.

The resulting dense solid support materials or microbeads may be subsequently coated or filled with an interacting polymer network comprised of various organic
15 polymers in order to confer specific biomolecule adsorption properties to the solid support materials or microbeads.

Example 9:**Preparation of highly dense microbeads with reduced
pore volume composed of a mixture of tantalia and zirconia**

Microbeads are prepared as described in Example 2 except that zircon fine powder is replaced by a 50%/50% mixture in weight of fine powders of tantalum oxide and zirconium oxide. The dried microbeads obtained are then fired at 1400°C
20 for 4 hours to reduce the initial pore volume (about 1/3 of bead volume) to about 15% of bead volume.

25 The density shown by these beads is about 6.2 g/cm³.

The resulting dense solid support materials or microbeads may be subsequently coated or filled with an interacting polymer network comprised of various organic polymers in order to confer specific biomolecule adsorption properties to the solid support materials or microbeads.

30

Example 10:**Preparation of highly dense microbeads with reduced pore volume composed of a mixture of zirconia and hafnia**

Microbeads are prepared as described in Example 9 except that the
5 composition of the mixture of fine powders in weight is 50% zirconium oxide and 50% hafnium oxide fine powders. The dried microbeads obtained are then fired at 1400°C for 4 hours to reduce the initial pore volume (about 1/3 of bead volume) to about 25% of bead volume.

The density shown by these beads is about 7 g/cm³.

10 The resulting dense solid support materials or microbeads may be subsequently coated or filled with an interacting polymer network comprised of various organic polymers in order to confer specific biomolecule adsorption properties to the solid support materials or microbeads.

Example 11:

15 **Preparation of collapsed porous mineral oxides microbeads by spray drying**

The mineral oxide microparticles in suspension in a solution of sodium silicate as described above in Examples 1 to 10 above are used directly for the preparation of microbeads by spray drying. The suspension is injected into a vertical drying chamber
20 through an atomization device, such as a revolving disk, a spray nozzle or an ultrasonic nebulizer, together with an hot gas stream, preferably air or nitrogen. The hot gas stream causes the rapid evaporation of water from the microdroplets. The hot gas stream is typically injected at a temperature of about 300°C to 350°C and exits the dryer at a temperature of slightly above 100°C.

25 Sodium silicate acts as a binder for the consolidation of individual aggregated mineral oxide microparticles. The dry microbeads obtained are then fired at a temperature which equals or exceeds the melting temperature of the mineral oxide(s) used to form the microbeads in order to irreversibly consolidate the mineral oxide network. This operation also results in the reduction of the pore volume of the beads
30 to less than about thirty percent, and preferably to about 5% to 25% of the bead volume.

The densities of mineral oxide solid supports or microbeads obtained by spray drying methods are similar to those indicated on Examples 1 through 10.

The resulting dense solid support materials or microbeads may be subsequently coated or filled with an interacting polymer network comprised of various organic polymers in order to confer specific biomolecule adsorption properties to the solid support materials or microbeads.

5

Example 12:

**Preparation of highly dense mineral oxide
microbeads by spray drying with reduced pore volume**

Microbeads are prepared according to Example 11 except that instead of sodium silicate solution, nitrates or sulfates of the same mineral oxide particles used to
10 prepare the beads are used as the binder.

The resulting dense solid support materials or microbeads may be subsequently coated or filled with an interacting polymer network comprised of various organic polymers in order to confer specific biomolecule adsorption properties to the solid support materials or microbeads.

15

Example 13:

**Preparation of highly dense microbeads with reduced
pore volume and enhanced external surface area**

Spherical beads which have a rough surface have a higher external surface area than smooth beads. This example describes a method of preparing solid support
20 materials or microbeads according to the present invention having a rough surface.

Microbeads are prepared according to Examples 1 to 12 described above except that the initial mineral oxide microparticles or powder used in the aqueous slurry have particle sizes in the range of 3 μm to 15 μm . When small dense mineral oxide solid supports or microbeads are made according to any of the methods
25 described herein using starting materials having large particle sizes, the resulting solid supports or microbeads have a very rough surface and the total external area is therefore increased.

Once these solid supports or microbeads are collapsed (by the firing or calcination step) and are provided with an interactive polymer network, e.g., such as
30 described in Examples 14 to 20 below, these solid support materials or microbeads show similar densities to the mineral oxide starting material used, and demonstrate increased binding capacity proportional to their external surface area. Typically, when the small dense mineral oxide solid supports or microbeads of the present invention are

made with rough surfaces, the surface area as well as the binding capacities of the solid supports or microbeads are increased by about 5% to 30%.

Example 14:

Dextran coated highly dense zirconium oxide beads

5 A solution of 1N sodium hydroxide is slowly added to 13 ml of an aqueous solution of 10% dextran (10,000 daltons molecular weight) until a pH of 11.5 is obtained. Then, sodium carbonate is added up to the concentration of 0.2M, and the solution is cooled to 4°C. To the final mixture, 1% of butanedioldiglycidylether is added. The resulting solution is immediately added to 100 ml of settled small dense
10 zirconium oxide microbeads having diameters in the range of 10µm to 100µm and a pore volume of about 12% of the total bead volume, such as those prepared in Example 6, in order to impregnate the microbeads with dextran.

 The resulting impregnated microbeads are transferred into a closed vessel and heated at 85°C overnight. Under these conditions, the dextran solution is crosslinked
15 in place rooted within the pores of the mineral oxide solid support, thereby filling the pores of the solid support media and creating a three dimensional interacting polymer network of dextran which is rooted in the pores and coats the external surface of the solid support materials or microbeads.

 The resulting solid supports or microbeads contain about 0.25 (wt)% sugars,
20 and can be used in classical chromatography media synthesis methods for the attachment of ion exchanger, hydrophobic, as well as affinity chemical groups.

Example 15:

Passivation of the surface of titania beads

 Mineral oxide surfaces have innate hydroxyl groups as well as Lewis acid sites
25 that are responsible for non-specific binding for biomolecules. The nature of these surfaces vary depending on the metal oxide and can be acidic, alkaline or both. In order to eliminate non-specific binding, special polymers can be used as passivating agents and stabilized irreversibly in place by a chemical crosslinking.

 The surface of titanium oxide microbeads is almost alkaline and as a result will
30 adsorb acidic proteins, for instance. In order to avoid non-specific binding of such molecules, passivation of the surface of these microbeads was accomplished by incubating the microbeads in 1 volume of an aqueous solution of hyaluronic acid,

which is well known for its non-adhesive properties. After washing to eliminate excess hyaluronic acid, the microbeads were dried and incubated with 0.5 volume of a solution containing 1% butanedioldiglycidylether in ethanol and 10 % of 1N sodium hydroxide. The suspension was incubated overnight, and then washed extensively.

5 The resulting passivated titanium oxide solid supports or microbeads may be used for subsequent applications.

The resulting dense solid support materials or microbeads may be subsequently coated or filled with an interacting polymer network comprised of various organic polymers in order to confer specific biomolecule adsorption properties to the solid support materials or microbeads.

10

Example 16:

Highly dense mineral oxide beads with pore volume filled with agarose

15 An agarose solution is obtained by dispersing 4 grams of agarose powder in water at 60°C to 80°C under vigorous stirring. A clear solution is obtained by heating the solution in a boiling bath for about 20 to 30 minutes. The agarose solution has the property to form reversible strong gels when cooled below 40°C.

Mineral oxide (e.g., hafnium oxide, zirconium oxide, titanium oxide, and the like) solid supports or microbeads, prepared as in Examples 1-13 and 15, are heated at about 150°C in a closed vessel, and then impregnated with a volume of the hot agarose solution, wherein the amount of hot agarose solution used roughly corresponds to 110% of the pore volume of the mineral oxide solid supports or microbeads. The resulting mixture is kept at 80-120°C for 1-2 hours, and then progressively cooled to room temperature. As a result, the agarose solution inside the pore volume of the microbeads and close to the surface of the microbeads is gelified and forms an organic, interactive polymer network which is ideal for the preparation of a large variety of derivatives for liquid chromatography using classically described chemical reactions.

20

25

Example 17:

30 **Highly dense porous mineral oxide beads filled with cellulose.**

A solution of cellulose triacetate is prepared by dispersion in acetone. The concentration of cellulose can typically be from 0.1 to 5% by weight. Other solvents well known to the skilled artisan can also be used for dissolving cellulose triacetate.

Mineral oxide (e.g., hafnium oxide, zirconia, titania, and the like) solid supports or microbeads, such as those prepared in Examples 1-13 and 15, are placed in a closed vessel and impregnated with a volume of cellulose triacetate solution, wherein the amount of cellulose triacetate solution used roughly corresponds to 110% of the pore volume of the mineral oxide solid supports or microbeads. The resulting mixture is stirred for 1-2 hours, and then the vessel is opened and the solvent evaporated slowly by an air stream.

Cellulose triacetate is deposited within the pore volume and the external surface area of the mineral oxide microbeads and forms an hydrophobic organic network. The cellulose triacetate is then turned into pure cellulose by mixing the solid phase (mineral oxide microbeads containing the cellulose derivative) with 0.5-2 M sodium hydroxide. The triacetate is hydrolyzed and cellulose is therefore regenerated. Cellulose is not soluble in aqueous environment, remains rooted inside the mineral oxide beads, and constitutes an ideal matrix for a number of derivatizations, such as the introduction of ion exchange groups or affinity or hydrophobic groups after appropriate chemical activation reactions well known to the skilled artisan are performed.

Example 18:

Immobilization of Concanavalin A on a highly dense agarose-zirconium oxide derivative.

Agarose-zirconium oxide solid supports or microbeads, prepared according to Examples 6 and 16, are first dried by repeated washings with dioxane to eliminate all traces of water. The dried microbeads are then drained and 10 grams of the drained cake of this material is suspended in 25 ml of pure dioxane and 1 gram of carbonyldiimidazole (CDI) is added. The resulting mixture is shaken for 4 hours at room temperature and then washed extensively with dioxane to eliminate the excess of reagents. The resulting CDI-activated material is mixed with 5 ml of 10 mg/ml Concanavalin A dissolved in 0.2 M carbonate buffer at pH 10. The mixture is gently agitated overnight and finally washed extensively with water and a 25 mM phosphate buffer containing 0.5M NaCl pH 7.2.

The resulting dense agarose-zirconium oxide solid supports or microbeads having Concanavalin A attached chemically on the surface show a binding capacity for ovalbumin of about 5 mg/ml.

Example 19 :**Preparation of highly dense anion
exchanger by filling polymerization**

5 grams of dimethyl-acrylamide, 0.5 grams of N,N'-methylene-bis-
5 methacrylamide and 5 grams of methacrylamidopropyltrimethyl-ammonium chloride
are dissolved in 50 ml of dimethylsulfoxide. 50 ml of distilled water are added and
mixed thoroughly, and then 0.2 grams of azo-bis-amidino-propane is added to the
mixture. The resulting monomer solution is mixed with a given amount of a dry dense
mineral oxide solid support or microbead prepared as in any of Examples 1-13 and 15,
10 such that the amount of microbeads used corresponds to a porous volume of 100 ml,
and the resulting mixture is mixed thoroughly and is placed in a closed vessel for 30-60
minutes.

The mixture is then heated for four hours at 70-90°C in order to initiate and
complete polymerization of the monomer mixture. At the end of the polymerization
15 reaction, the resulting dense ion exchanger solid supports or microbeads are washed
extensively, and may be used for chromatographic separation or isolation of proteins.

The number of ionic groups per ml of microbeads is about 65 μ moles and the
binding capacity for bovine serum albumin in classical conditions of ionic strength and
pH is about 25 mg/ml.

20

Example 20:**Preparation of highly dense cation
exchanger by filling polymerization**

5 grams of dimethyl-acrylamide, 0.5 grams of N,N'-methylene-bis-
methacrylamide and 5 grams of acrylamidomethyl-propane sulfonic acid sodium salt
25 are dissolved in 50 ml of dimethylsulfoxide. 50 ml of distilled water are added and
mixed thoroughly, and then 0.2 grams of azo-bis-amidino-propane is added to the
mixture. The resulting monomer solution is mixed with a given amount of dry dense
mineral oxide solid support or microbead prepared as in any of Examples 1-13 and 15,
such that the amount of microbeads used corresponds to a porous volume of 90 ml,
30 and the resulting mixture is mixed thoroughly and is placed in a closed vessel for 30-60
minutes.

The mixture is then heated for four hours at 70-90°C in order to initiate and
complete polymerization of the monomer mixture. At the end of the polymerization

reaction, the resulting dense ion exchanger or microbeads are washed extensively, and may be used for chromatographic separation or isolation of proteins.

The number of ionic groups per ml of microbeads is about 60 μ moles and the binding capacity for lysozyme in classical conditions of ionic strength and pH is about 35 mg/ml.

Example 21:

Measurement of binding capacity for a large protein of an anionic exchanger of different particle size

Anion exchanger solid supports are prepared according to Example 17, wherein the mineral oxide matrix comprises zirconium oxide having pore volume of about 12% of the bead volume. The density shown by these beads is about 5.2 g/cm³.

Various particle diameters of the resulting zirconium oxide solid supports having cellulose as the interactive polymer network are isolated by sieving; specifically, the particle diameters isolated are about 10 μ m, 20 μ m, 40 μ m, and 80 μ m.

The binding capacities of these different size particles are measured for the large macromolecules thyroglobulin (mw 670,000 daltons) and a 10 kb plasmid. Binding capacity is measured by breakthrough ("BT") curve method and calculations made at 10% breakthrough.

Binding capacity at 10% BT (mg/ml) for different particle sizes and two macromolecules:

	10 μ m particles	20 μ m particles	40 μ m particles	80 μ m particles
Thyroglobulin	60 mg/ml	27 mg/ml	15 mg/ml	8 mg/ml
Plasmid	13 mg/ml	5.8 mg/ml	2.5 mg/ml	1.8 mg/ml

Binding capacity of the dense mineral oxide supports or microbeads of the present invention is believed to be dependent on the particle size, and it is believed that binding is essentially displayed on the surface of these solid supports or microbeads.

Example 22:**Fluidization properties of various
porous dense microspheres of mineral oxides**

Three types of mineral oxide beads are prepared according to the procedure
5 described in Example 12.

Specifically, a sodium silicate solution is prepared by mixing 150 grams of a
35% commercial silicate solution in 400 ml of distilled water. Similarly, a titanyl
sulfate solution is prepared by mixing 30 grams of titanyl sulfate in 400 ml of distilled
water, and a zirconyl nitrate solution is prepared by mixing 150 grams of a 20%
10 zirconyl nitrate solution in 400 ml of distilled water.

273 grams of dry solid irregular silicon oxide (having particle sizes in the range
of 0.3-5 μm) are then added to the sodium silicate solution under gentle stirring to
prevent the introduction of air bubbles. Similarly, 275 grams of titanium oxide fine
powder (having particle sizes in the range of 0.1- 10 μm) are added to the titanyl
15 sulfate solution under gentle stirring, and 275 grams of zirconium oxide fine powder
(having particle sizes in the range of 0.1-3 μm) are added to the zirconyl nitrate
solution under gentle stirring.

The resulting suspensions are then each independently injected into a Sodeva
Atselab spray dryer (commercially available from Sodeva, Le bouget du Lac, France),
20 together with a hot air stream. The hot air stream is injected concurrently with the
suspension into the vertical drying chamber at a temperature of about 350°C, and exits
the drying chamber at a temperature of about 98°C.

Each of the three types of dried mineral oxide microbeads obtained with this
methodology are then calcined at 1400°C for 4 hours to reduce the pore volume to
25 about 10-15% of the bead volume.

The mean particle diameter of the resulting mineral oxide solid supports
or microbeads is measured by laser-diffraction spectrometry (Malvern particle
sizer).

The fluidization behaviors of the different particles are investigated in a
30 2.5 ID classical fluidized bed column, using distilled water as the mobile phase.
The velocity which allows a two time bed expansion of the bed of each type of
mineral oxide solid supports or microbeads prepared as indicated above are as
follow:

materials	SiO ₂	TiO ₂	ZrO ₂
mean particle diameter (μm)	65	60	65
specific density (g/cm^3)	1.78	2.9	4.6
linear velocity (cm/h) at 2 time bed expansion	136	285	630

Increased density positively impacts the operating velocity at a two times bed expansion. This has a beneficial effect on the column productivity and
 5 furthermore decreases the risks associated with the denaturation of biological material.

Example 23:

Capture of IgM from a serum fraction using a Concanavalin A derivative of highly dense zirconium oxide microbeads

10 20 grams of highly dense Concanavalin A-agarose-zirconium oxide solid supports or microbeads, prepared according to Examples 6, 16 and 18, are mixed with 50 ml of 50 mM Tris-HCl buffer pH 7.8, containing 2 mM MnCl₂.

In parallel, 200 ml of frozen human plasma or serum sample are thawed and filtered to eliminate cryoprecipitate. Large proteins are precipitated from the sample
 15 by adding pure ethanol up to a final concentration of 15% in volume. After agitating for about 20 minutes at room temperature, the precipitate is recovered by centrifugation and dissolved in 1 liter of 50 mM Tris-HCl buffer pH 7.8, containing 2 mM MnCl₂.

The resulting sample solution, which is not completely clear and contains some
 20 material which does not dissolve, is introduced into a fluid bed device already loaded with the microbead suspension equilibrated in 50 mM Tris-HCl buffer pH 7.8, 2 mM MnCl₂. An upward buffer flow which maintains the beads at a 2 times bed expansion is applied. Once the sample has been completely supplied to the device, a 50 mM Tris-

HCl pH 7.8, 2 mM MnCl_2 buffer is introduced to wash out all insoluble particles, and then non-specifically adsorbed materials are eluted by adding 0.5 M sodium chloride to the washing buffer.

IgM, which are known for their affinity for Concanavalin A (the glycosylated moiety of IgM interacts specifically with Concanavalin A), are selectively desorbed from the solid supports or microbeads by replacing the washing buffer with an elution buffer composed of 50 mM Tris-HCl buffer pH 7.8, 2 mM MnCl_2 and 20 mM of α -methyl-glucopyranoside. After collection of the IgM is completed, the column is then equilibrated with the initial buffer, *i.e.*, 50 mM Tris-HCl buffer pH 7.8, 2 mM MnCl_2 and then can be reused for another separation cycle.

Example 24:

Hepatitis B virus capture using a Cibacron Blue derivative of highly dense Titanium oxide microbeads

20 grams of highly dense agarose-titanium oxide solid supports or microbeads, prepared according to Examples 3 and 16, are suspended in 50 ml of 50 mM carbonate buffer pH 11.5 containing 0.5 M sodium chloride. To this suspension 2 grams of Cibacron Blue 3GA (a triazine reactive dye known for its affinity for Hepatitis B virus, commercially available from Sigma Chemicals, St. Louis, Missouri, USA) are added and the suspension is shaken overnight at room temperature. The suspension is then heated at 60°C for about an hour, and then the suspension washed extensively to eliminate any excess of Cibacron Blue 3GA dye molecules.

The resulting slurry is introduced into a fluid bed device of 2.5 cm diameter and continuously maintained in suspension by an upward flow of a phosphate buffered saline. A human immunoglobulin sample solution containing hepatitis B viruses in physiological buffer is then introduced into the column from the bottom at a linear velocity which maintains the solid supports or microbeads in fluidized state. Viruses are captured by the Cibacron Blue functionalized agarose-titanium oxide solid supports or microbeads, while the virus-depleted immunoglobulin sample solution is collected from the top of the column. The Cibacron Blue functionalized agarose-titania solid supports or microbeads are then washed with sodium hydroxide and other sterilizing solutions so as to eliminate and inactivate the adsorbed viruses, and then reequilibrated with the initial loading buffer such that other separation cycles may be performed.

Virus clearance according to this example can be on the order of about 4 logs.

Example 25:**Capture of plasmids from a *E. coli* crude extract using a quaternary amino derivative of highly dense zirconium oxide microbeads**

5 50 grams of highly dense anion exchanger-zirconium oxide solid supports or microbeads, prepared according to Examples 6 and 19, are suspended in 100 ml of 50 mM Tris-HCl, 500 mM NaCl buffer pH 8.5 and introduced into a fluid bed column of 25 mm diameter and maintained in suspension by an upward flow at a speed high enough to prevent microbeads from settling and maintains the microbeads in a fluidized state.

10 In parallel an *E. coli* lysate obtained using classical alkaline-SDS treatment (0.2 M NaOH, 1%-SDS) is subject to various alcoholic precipitations (Green *et al.*, "Preparative purification of supercoiled plasmid DNA for therapeutic applications," *Biopharm*, pp. 52-62 (May 1997)) in order to eliminate proteins, is diafiltered against 50 mM Tris-HCl, 500 mM NaCl pH 8.5 buffer and the resulting lysate sample is
15 introduced into the column from the bottom end, at the same linear velocity which prevents the microbeads from settling and maintains the microbeads in a fluidized state.

The dense microbeads in suspended in the fluidized bed adsorb most of nucleic acid molecules in the lysate sample, except for small fragments. The fluid bed suspension is then washed with the same working buffer in order to eliminate unbound
20 contaminants. Then, a 50 mM Tris-HCl pH 8.5 buffer containing 680 mM NaCl is used to wash out RNA molecules. Thereafter, plasmid molecules are specifically eluted in fluidized bed mode, by increasing the NaCl concentration in the buffer to 1000 mM. Finally, strongly bound contaminants, such as genomic DNA, are desorbed from the microbeads by cleaning in the fluid mode using an 0.5 M sodium hydroxide
25 solution. The column is then reequilibrated with 50 mM Tris-HCl, 500 mM NaCl buffer pH 8.5 such that another cycle may be performed.

The purity of the plasmids obtained with this fluid bed process is comparable to that obtained using a similar cationic solid phase packed in a fixed bed column. However, in the present example, elution is easier since in fluid bed mode the viscosity
30 of the plasmid sample does not limit the flow rate of the column, as is the case in a packed bed mode.

It should be apparent to those skilled in the art that other compositions and methods not specifically disclosed in the instant specification are, nevertheless,

contemplated thereby. Such other compositions and methods are considered to be within the scope and spirit of the present invention. Hence, the invention should not be limited by the description of the specific embodiments disclosed herein by only by the following claims.

What is claimed is:

1. Dense mineral oxide solid supports comprising
 - a) a mineral oxide matrix having a pore volume which is less than 30% of the total volume of the mineral oxide matrix, and
 - b) an interactive polymer network which is rooted in pores and on the surface of the mineral oxide matrix.
2. The dense mineral oxide solid supports of Claim 1, having a density in the range of about 1.7 to 11.
3. The dense mineral oxide solid supports of Claim 2, wherein the density is in the range of about 2.1 to about 10.
4. The dense mineral oxide solid supports of Claim 1 or 2, wherein said dense mineral oxide solid supports have a particle size in the range of about 5 μm to about 500 μm .
5. The dense mineral oxide solid supports of Claim 4, wherein the particle size is in the range of about 10 μm to about 100 μm .
6. Dense mineral oxide solid supports comprising
 - a) a mineral oxide matrix having a pore volume which is less than 30% of the total volume of the mineral oxide matrix, and
 - b) an interactive polymer network which is rooted in pores and on the surface of the mineral oxide matrix,wherein said dense mineral oxide solid supports have a density of 2.1 to 11, and a particle size of 10 μm to 100 μm .
7. The dense mineral oxide solid supports of Claims 1 or 6, wherein the pore volume is 5 % to 25 % of the total volume of the mineral oxide matrix.
8. The dense mineral oxide solid supports of Claim 7, wherein the pore volume is 5% to 15%.

9. The dense mineral oxide solid supports of Claims 1 or 6, wherein the mineral oxide matrix is comprised of titania, zirconia, yttria, ceria, hafnia, tantalum, or mixtures thereof.

5 10. The dense mineral oxide solid supports of Claims 1 or 6, wherein the interactive polymer network comprises a soluble organic polymer or a mixture of soluble organic polymers crosslinked in place with the mineral oxide matrix.

10 11. The dense mineral oxide solid supports of Claim 10, wherein the soluble organic polymer is a polysaccharide or a mixture of polysaccharides.

12. The dense mineral oxide solid supports of Claim 11, wherein the polysaccharide is selected from the group consisting of agarose, dextran, cellulose, chitosan, a glucosaminoglycan, and derivatives thereof.

15 13. The dense mineral oxide solid supports of Claim 10, wherein the soluble organic polymer is a linear soluble organic polymer selected from the group consisting of polyvinyl alcohol, a polyethyleneimine, a polyvinylamine, polyvinylpyrrolidone, a polyethyleneglycol, a polyaminoacid, a nucleic acid, and
20 derivatives thereof.

14. The dense mineral oxide solid supports of Claims 1 or 6, wherein the interactive polymer network comprises monomers, bifunctional monomers, or mixtures thereof copolymerized in place with the mineral oxide matrix.

25 15. The dense mineral oxide solid supports of Claim 14, wherein the monomers are selected from the group consisting of:

- (a) aliphatic ionic, non-ionic, and reactive derivatives of acrylic, methacrylic, vinylic, and allylic compounds;
- 30 (b) aromatic ionic, non-ionic, and reactive derivatives of acrylic, methacrylic, vinylic, and allylic compounds;
- (c) heterocyclic ionic, non-ionic, and reactive derivatives of acrylic, methacrylic, vinylic, and allylic compounds; and
- (d) mixtures of any of the monomers in (a), (b) or (c).

35

16. The dense mineral oxide solid supports of Claim 15, wherein (a) is acrylamide, dimethylacrylamide, trisacryl, acrylic acid, acryloylglycine, diethylaminoethyl methacrylamide, vinylpyrrolidone, vinylsulfonic acid, allylamine, allylglycidylether, or derivatives thereof.

17. The dense mineral oxide solid supports of Claim 15, wherein (b) is vinyltoluene, phenylpropylacrylamide, trimethylaminophenylbutylmethacrylate, tritylacrylamide, or derivatives thereof.

18. The dense mineral oxide solid supports of Claim 15, wherein (c) is vinylimidazole, vinylpyrrolidone, acryloylmorpholine, or derivatives thereof.

19. The dense mineral oxide solid supports of Claim 14, wherein the bifunctional monomers are selected from the group consisting of:

- (a) bisacrylamides;
- (b) bis-methacrylamides;
- (c) bis-acrylates;
- (d) ethyleneglycol-methacrylates; and
- (e) diallyltartradiamide.

20. The dense mineral oxide solid supports of Claim 19, wherein (a) is N,N'-methylene-bis-acrylamide, N,N'-ethylene-bis-acrylamide, N,N'-hexamethylene-bis-acrylamide, or glyoxal-bis-acrylamide.

21. The dense mineral oxide solid supports of Claim 19, wherein (b) is N,N'-methylene-bis-methacrylamide, N,N'-ethylene-bis-methacrylamide, or N,N'-hexamethylene-bis-methacrylamide.

22. The dense mineral oxide solid supports of Claim 19, wherein (c) is ethyleneglycoldiacrylate, or ethyleneglycoldimethacrylate.

23. A method of separating a target molecule by solid phase adsorption comprising passing a sample containing said target molecule through a chromatography device loaded with a solid phase matrix comprising the dense mineral oxide solid supports of Claim 1 or Claim 6.

24. The method of Claim 23, wherein the target molecule is a biological molecule.

25. A method for separating a desired biological molecule from a sample
5 solution containing the same comprising the steps of :

a) loading a chromatography device with a chromatography bed
comprised of dense mineral oxide solid supports comprising

i) a mineral oxide matrix having a pore volume which is less than 30%
of the total volume of the mineral oxide matrix, and
10 ii) an interactive polymer network which is rooted in pores and on the
surface of the mineral oxide matrix, wherein the interactive polymer
network is functionalized to have affinity for the desired biological
molecule;

b) feeding the sample solution containing said desired biological
15 molecule into the chromatography device, whereby the desired biological molecule is
adsorbed to the dense mineral oxide solid supports;

c) washing the chromatography device with a washing buffer and
discharging undesired components and impurities of the sample solution from the
chromatography device;

20 d) feeding an eluting buffer into the chromatography device, wherein said
eluting buffer causes the desired biological molecule to be released from the dense
mineral oxide solid supports; and

e) collecting the desired biological molecule.

25 26. The method of Claim 25, wherein the dense mineral oxide solid
supports have a density in the range of about 2.1 to about 11.

27. The method of Claim 25 or 26, wherein said dense mineral oxide solid
supports have a particle size in the range of about 5 μm to about 500 μm .

30 28. The method of Claim 27, wherein the particle size is about 10 μm to
about 100 μm .

29. The method of Claim 25, wherein the mineral oxide matrix is
35 comprised of titania, zirconia, yttria, ceria, hafnia, tantalia, or mixtures thereof.

30. The method of Claim 28, wherein the mineral oxide matrix is comprised of titania, zirconia, yttria, ceria, hafnia, tantalia, or mixtures thereof

31. The method of Claim 25, wherein the interactive polymer network
5 comprises a soluble organic polymer or a mixture of soluble organic polymers crosslinked in place with the mineral oxide matrix.

32. The method of Claim 25, wherein the interactive polymer network comprises monomers, bifunctional monomers, or mixtures thereof copolymerized in
10 place with the mineral oxide matrix.

33. The method of Claim 25, wherein the desired biological molecule is a macromolecule.

15 34. The method of Claim 33, wherein the macromolecule is a polysaccharide, a plasmid, a nucleic acid, a polynucleotide, or a protein aggregate.

35. The method of Claim 25, wherein the desired biological molecule is a bioparticle.

20 36. The method of Claim 35, wherein the bioparticle is a virus, a viral vector, a membrane protein, or a cellular structure.

37. The method of Claim 25, wherein the chromatography device is a
25 packed bed column, a fluidized bed column, or a continuous stirred tank.

38. A fluidized bed chromatography method for separating a desired biological molecule from a sample solution containing the same comprising the steps of:

- a) loading a fluidized bed column with a chromatography bed comprised of dense mineral oxide solid supports comprising
 - i) a mineral oxide matrix having a pore volume which is less than 30% of the total volume of the mineral oxide matrix, and
 - ii) an interactive polymer network which is rooted in pores and on the surface of the mineral oxide matrix, wherein the interactive polymer network is functionalized to have affinity for the desired biological molecule;
- b) feeding an initial buffer into said fluidized bed column at a linear velocity which causes the dense mineral oxide solid supports to form a fluidized bed;
- c) feeding the sample solution containing said desired biological molecule into the fluidized bed column at a linear velocity which maintains the dense mineral oxide solid supports in the fluidized bed, whereby the desired biological molecule is adsorbed to the dense mineral oxide solid supports;
- d) washing the chromatography device with a washing buffer and discharging undesired components and impurities of the sample solution from the fluidized bed column device;
- e) feeding an elution buffer into the fluidized bed column, wherein said elution buffer causes the desired biological molecule to be released from the dense mineral oxide solid supports; and
- f) collecting the desired biological molecule eluted from the fluidized bed column.

39. The method of Claim 38, wherein the dense mineral oxide solid supports have a density in the range of about 2.1 to about 11.

40. The method of Claim 38 or 39, wherein said dense mineral oxide solid supports have a particle size in the range of about 5 μm to about 500 μm .

41. The method of Claim 40, wherein the particle size is about 10 μm to about 100 μm .

42. The method of Claim 38, wherein the mineral oxide matrix is comprised of titania, zirconia, yttria, ceria, hafnia, tantalum, or mixtures thereof.

5 43. The method of Claim 41, wherein the mineral oxide matrix is comprised of titania, zirconia, yttria, ceria, hafnia, tantalum, or mixtures thereof.

44. The method of Claim 38, wherein the interactive polymer network comprises a soluble organic polymer or a mixture of soluble organic polymers
10 crosslinked in place with the mineral oxide matrix.

45. The method of Claim 38, wherein the interactive polymer network comprises monomers, bifunctional monomers, or mixtures thereof copolymerized in place with the mineral oxide matrix.

15 46. The method of Claim 38, wherein the desired biological molecule is a macromolecule.

47. The method of Claim 46, wherein the macromolecule is a
20 polysaccharide, a plasmid, a nucleic acid, a polynucleotide, or a protein aggregate.

48. The method of Claim 38, wherein the desired biological molecule is a bioparticle.

25 49. The method of Claim 48, wherein the bioparticle is a virus, a viral vector, a membrane protein, or a cellular structure.

50. The fluidized bed chromatography method of Claim 38, wherein the linear velocity is within the range of 100 cm/hour to 3000 cm/hour.

30

51. A method for preparing dense mineral oxide solid supports which comprises:

- (a) preparing a mixture of particles of at least one mineral oxide;
- (b) forming a mineral oxide matrix from said mixture;
- 5 (c) sintering the resulting mineral oxide matrix at a high temperature which melts subparticles in the mineral oxide matrix, wherein the sintering reduces the pore volume of the mineral oxide matrix to less than 30% of the total volume of the mineral oxide matrix; and
- (d) forming an interactive polymer network rooted in the pores and on the
10 surface of the resulting sintered mineral oxide matrix.

52. The method of Claim 51, wherein the mineral oxide is selected from the group consisting of titania, zirconia, yttria, ceria, hafnia, tantalum, or mixtures thereof

15

53. The method of Claim 51, wherein the particles of mineral oxide have a particle size of in the range of 0.1 μm to 15 μm .

54. The method of Claim 53, wherein the particles of mineral oxide have a
20 particle size of 0.1 μm to 3 μm .

55. The method of Claim 51, wherein the dense mineral oxide solid supports have a rough surface, and wherein the particles of mineral oxide have a particle size of 3 μm to 15 μm .

25

56. The method of Claim 51, wherein the beads are formed by a sol-gel process, a spray drying process, or an emulsion-polycondensation process.

57. The method of Claim 51, wherein the interactive polymer network is
30 comprised of monomers, bifunctional monomers, or mixtures thereof copolymerized in place with the mineral oxide matrix.

58. The method of Claim 51, wherein the interactive polymer network is comprised of a soluble organic polymer or a mixture of soluble organic polymers
35 crosslinked in place with the mineral oxide matrix.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/07480

A. CLASSIFICATION OF SUBJECT MATTER		
IPC 6	B01D15/08	B01J20/00 B01J8/18 B01J8/10 B01D15/02
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols)		
IPC 6 B01D B01J G01N		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 635 301 A (UNIV MINNESOTA) 25 January 1995 (1995-01-25) page 2, line 1-18 page 4, line 1-24	1,4,5, 7-18, 23-25, 29-32, 34,51-58
Y	US 5 567 615 A (DEGEN PETER J ET AL) 22 October 1996 (1996-10-22) column 2, line 51 - column 4, line 50	1-58
Y	US 5 470 463 A (GIROT PIERRE ET AL) 28 November 1995 (1995-11-28) column 4, line 51 - column 11, line 32 -/--	1-58
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents : "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "A" document member of the same patent family		
Date of the actual completion of the international search		Date of mailing of the international search report
22 July 1999		30/07/1999
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer Persichini, C

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/07480

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 486 293 A (BOSCHETTI EGISTO ET AL) 23 January 1996 (1996-01-23) the whole document -----	1-58
A	US 5 372 820 A (JOZEFONVICZ NEE DORGEBRAY JACQ ET AL) 13 December 1994 (1994-12-13) the whole document -----	1-58

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/07480

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0635301 A	25-01-1995	DE 69112460 D	05-10-1995
		DE 69112460 T	28-03-1996
		EP 0448302 A	25-09-1991
		JP 4228427 A	18-08-1992
		US 5182016 A	26-01-1993
		US 5271833 A	21-12-1993
US 5567615 A	22-10-1996	CA 2127605 A	24-06-1995
		CN 1107748 A	06-09-1995
		DE 4445517 A	29-06-1995
		DK 142194 A	24-06-1995
		FR 2714299 A	30-06-1995
		GB 2287662 A, B	27-09-1995
		JP 7265606 A	17-10-1995
		NL 9402136 A	17-07-1995
US 5470463 A	28-11-1995	SE 9404250 A	24-06-1995
		US 5599453 A	04-02-1997
		AU 681590 B	04-09-1997
		AU 4538493 A	24-01-1994
		CA 2138520 A	06-01-1994
		EP 0646038 A	05-04-1995
		JP 7509173 T	12-10-1995
		WO 9400214 A	06-01-1994
		US 5393430 A	28-02-1995
		US 5445732 A	29-08-1995
		US 5593576 A	14-01-1997
		US 5672276 A	30-09-1997
		US 5906734 A	25-05-1999
		US 5268097 A	07-12-1993
US 5486293 A	23-01-1996	AU 688024 B	05-03-1998
		AU 2121795 A	09-10-1995
		CA 2196971 A	28-09-1995
		EP 0751810 A	08-01-1997
		JP 9512204 T	09-12-1997
		WO 9525574 A	28-09-1995
		US 5609763 A	11-03-1997
US 5372820 A	13-12-1994	FR 2635019 A	09-02-1990
		AT 74797 T	15-05-1992
		EP 0357479 A	07-03-1990
		GR 3004807 T	28-04-1993
		JP 2090943 A	30-03-1990